

## PRODUCT CHARACTERISTICS

### FORMAT

|                           |         |                |
|---------------------------|---------|----------------|
| Width                     | 192     | mm             |
| Length                    | 1261    | mm             |
| Number of panels per pack | 10      |                |
| m <sup>2</sup> per pack   | 2,421   | m <sup>2</sup> |
| Bevels                    | no      |                |
| Thickness                 | 7,0     | mm             |
| Tongue and groove         | Uniclic |                |

## PANEL BUILD-UP



1. Superior wear and scratch-resistance layer
2. Crystal-clear decor
3. Moisture-resistant HDF core
4. Back stabiliser

## FACTORY WARRANTY

|             | METHOD                        | PARAMETERS              |                     |                |
|-------------|-------------------------------|-------------------------|---------------------|----------------|
| Usage class | EN ISO 10874                  |                         | Class               | 21-22-23/31-32 |
| CE          | EN 14041:2004+AC:2005+AC:2006 | Notified body           | NB 0493 - Centexbel | DOP: On pack   |
| UKCA        | EN 14041:2004+AC:2005+AC:2006 | Approved Body           | AB 8515 - Centexbel | DOP: On pack   |
| Warranty    | Residential use               | See warranty conditions | 15                  | years          |
|             | Commercial use                | See warranty conditions | 5                   | years          |

## GENERAL DATA (ACCORDING TO EN 13329)

|                                                           | METHOD                                              | PARAMETERS                  | NORM REQUIREMENTS                                        |           |
|-----------------------------------------------------------|-----------------------------------------------------|-----------------------------|----------------------------------------------------------|-----------|
| Abrasion resistance                                       | ISO 24338 - Prodecure A                             |                             | ≥ 4000                                                   | cycles    |
| Abrasion class                                            | EN 13329                                            |                             | AC4                                                      |           |
| Impact resistance                                         | EN 17368                                            | Small ball                  | ≥ 35 mm                                                  |           |
|                                                           | EN 13329                                            | Big ball                    | ≥ 600 mm                                                 |           |
| Scratch resistance                                        | EN 438-2, 25                                        |                             | Charge                                                   | ≥ 3N      |
| Effect of a castor chair                                  | EN ISO 4918 (with underlay)                         | Type W (EN 12529)           | 15000                                                    | cycles    |
| Thickness swelling                                        | ISO 24336                                           | after 24h immersion at 20°C | ≤ 18%                                                    |           |
| Locking strength                                          | ISO 24334                                           | Fl0,2 long side             | ≥ 1 kN/m                                                 |           |
|                                                           |                                                     | Fmax long side              |                                                          |           |
|                                                           |                                                     | Fs0,2 short side            | ≥ 2 kN/m                                                 |           |
|                                                           |                                                     | Fmax short side             |                                                          |           |
| Effect of a furniture leg                                 | EN ISO 16581                                        |                             | No damage shall be visible, when tested with foot type 0 |           |
| Surface soundness                                         | EN 13329                                            | N/mm <sup>2</sup>           | ≥ 1,25                                                   |           |
| Static indentation                                        | EN ISO 24343-1                                      |                             | Residual indentation                                     | ≤ 0,05 mm |
| Resistance to staining                                    | EN 438-2                                            | Group 1, 2                  | Class                                                    | 5         |
|                                                           |                                                     | Group 3                     | Class                                                    | 4         |
| General appearance                                        | EN 13329                                            | Height differences          | ≤ 0,15 mm                                                |           |
|                                                           |                                                     | Opening between joints      | ≤ 0,20 mm                                                |           |
|                                                           |                                                     | Cupping in the length       | concave ≤ 0,50%                                          |           |
|                                                           |                                                     |                             | convex ≤ 1,00%                                           |           |
| Dimensional variations after changes in relative humidity | EN 13329                                            | δl                          | concave ≤ 0,15%                                          |           |
|                                                           |                                                     |                             | convex ≤ 0,20%                                           |           |
|                                                           |                                                     | δw                          | δl average ≤ 0,9 mm                                      |           |
|                                                           |                                                     |                             | δw average ≤ 0,9 mm                                      |           |
| Light fastness                                            | EN ISO 4892-2:2013 procedure B - cycle 2 or cycle 5 | Grey reference              | Class                                                    | ≥ 4       |

## GENERAL DATA (ACCORDING TO EN 13329)

|                  | METHOD   | PARAMETERS                             | NORM REQUIREMENTS | VALUES     |
|------------------|----------|----------------------------------------|-------------------|------------|
| Water resistance | ISO 4760 | Qualitative rating for Recovery swell  | < 3               | 1          |
|                  |          | Quantitative rating for Recovery swell | ≤ 0,3mm           | ≤ 0,01mm   |
|                  |          | Joint leakage                          | No requirement    | No leakage |

## OTHER TECHNICAL DATA

|                        | METHOD                                             | PARAMETERS         |                          |                              |
|------------------------|----------------------------------------------------|--------------------|--------------------------|------------------------------|
| Impact sound reduction | ISO 712/2                                          |                    | ΔLw ≤ 21dB               | (Depending on used underlay) |
| Floor heating          |                                                    |                    | See special instructions | Suitable                     |
| Formaldehyde emission  | EN 717-1                                           | ppm                | < E0,5                   |                              |
| Anti-static            | EN 1815                                            |                    | ≤ 2,0 kV                 |                              |
| Fire classification    | EN 13501-1                                         | Class              | Cfl-s1                   |                              |
| Thermal resistance     | EN 12667                                           | m <sup>2</sup> K/W | 0,051                    | m <sup>2</sup> K/W           |
| Slip resistance        | EN 13893                                           | μ                  | DS: μ ≥ 0,30             |                              |
|                        | EN 16165:2021-10 Annex B                           |                    | R12                      |                              |
|                        | UNE-EN 16165:2022 Annex C<br>Anexo Nacional A (ES) | Wet                | PTV <sub>cp</sub> ≥ 45   | Class 3                      |

## CERTIFICATES

|             |               |
|-------------|---------------|
| EU Ecolabel | SE/035/001    |
| AFFSET      | A+            |
| PEFC        | PEFC/07-32-37 |
| EPD         |               |

